

BESTRAP R95 SUPER (UNI EN 13246 Type 3.2)

LARGHEZZA Width (mm)	SPESSORE Thickness (mm)	SUPERFICIE Surface	CONFEZIONAMENTO Wound	RM Mpa2	m/Kg	ALLUNGAMENTO [A100%] Elongation [A100%]
19	0,50	B/BP/ZP/ZC	RW/OW/JC	≥ 925	13,5	min 6
	0,60	B/BP/ZP/ZC	RW/OW/JC	≥ 925	11,2	min 6
	0,70	B/BP/ZP/ZC	RW/OW/JC	≥ 925	9,6	min 6
	0,80	B/BP/ZP/ZC	RW/OW/JC	≥ 925	8,4	min 6
25	0,80	B/BP/ZP/ZC	RW/JC	≥ 925	6,4	min 6
	0,90	B/BP/ZP/ZC	RW/JC	≥ 925	5,7	min 6
32	0,80	B/BP/ZP/ZC	RW/JC	≥ 925	5,0	min 6
	0,90	B/BP/ZP/ZC	RW/JC	≥ 925	4,4	min 6

SUPERFICIE Surface	
B	Blu Blue
BP	Laccata Nera Black Painted
ZP	Zincata Verniciata Zinc Painted
ZC	Zincata a caldo Hot Galvanized

CONFEZIONAMENTO Wound	
RW	Monospira Ribbon
OW	Oscillata Oscillated
JC	Jumbo 200
	Jumbo 200
	Jumbo 400
	Jumbo 400
	Jumbo 1000
	Jumbo 1000